

GUARDIAN EUROPE S.A.R.L.
 19, rue du Puits Romain
 L-8070 Bertrange, Luxembourg

LamiGlass® 08mm

EN 14449:2005

Laminated Glass intended to be used in buildings and construction works values
 as of March 2007

	4.4.1	4.4.2	4.4.3	4.4.4	4.4.6	4.4.8
Resistance to fire	NPD	NPD	NPD	NPD	NPD	NPD
Reaction to fire	NPD	NPD	NPD	NPD	NPD	NPD
External fire performance	NPD	NPD	NPD	NPD	NPD	NPD
Bullet resistance	NPD	NPD	NPD	NPD	NPD	NPD
Explosion resistance	NPD	NPD	NPD	NPD	NPD	NPD
Burglar resistance	P1A	P2A	P3A	P4A	P5A	P6B
Pendulum body impact resistance	2(B)2	1(B)1	1(B)1	1(B)1	1(B)1	1(B)1
Resistance against sudden temperature changes and temperature differentials	K	40	40	40	40	40
Wind, snow, permanent and imposed load resistance	mm	8	8	8	8	8
Direct airborne sound insulation	dB	33 (-1;-3)	33 (-1;-3)	33 (-1;-3)	33 (-1;-3)	33 (-1;-3)
Thermal properties						
Thermal transmittance (U-value)	W/(m².K)	5.6	5.6	5.6	5.6	5.6
Radiation properties						
Light transmission τV		0.88	0.88	0.88	0.88	0.87
Light reflection pV		0.08	0.08	0.08	0.08	0.08
Solar energy transmission τE		0.75	0.74	0.73	0.71	0.70
Solar energy reflection pE		0.07	0.07	0.07	0.07	0.07