

GUARDIAN EUROPE S.A.R.L.
 19, rue du Puits Romain
 L-8070 Bertrange, Luxembourg

LamiGlass® 12mm

EN 14449:2005

Laminated Glass intended to be used in buildings and construction works values
 as of March 2007

	6.6.1	6.6.2	6.6.3	6.6.4	6.6.6	6.6.8	8.4.2
Resistance to fire	NPD	NPD	NPD	NPD	NPD	NPD	NPD
Reaction to fire	NPD	NPD	NPD	NPD	NPD	NPD	NPD
External fire performance	NPD	NPD	NPD	NPD	NPD	NPD	NPD
Bullet resistance	NPD	NPD	NPD	NPD	NPD	NPD	NPD
Explosion resistance	NPD	NPD	NPD	NPD	NPD	NPD	NPD
Burglar resistance	NPD	P2A	NPD	P4A	P5A / P6B Tudela	P6B	NPD
Pendulum body impact resistance	1(B)1	1(B)1	NPD	1(B)1	1(B)1	1(B)1	NPD
Resistance against sudden temperature changes and temperature differentials	K	40	40	40	40	40	40
Wind, snow, permanent and imposed load resistance	mm	12	12	12	12	12	12
Direct airborne sound insulation	dB	35 (-1;-3)	35 (-1;-3)	35 (-1;-3)	35 (-1;-3)	35 (-1;-3)	NPD
Thermal properties							
Thermal transmittance (U-value)	W/(m².K)	5.5	5.5	5.5	5.5	5.5	5.4
Radiation properties							
Light transmission τV		0.87	0.87	0.87	0.87	0.86	0.86
Light reflection pV		0.08	0.08	0.08	0.08	0.08	0.08
Solar energy transmission τE		0.70	0.69	0.68	0.66	0.65	0.64
Solar energy reflection pE		0.07	0.07	0.07	0.07	0.07	0.07